

Low Cement Castables—Standard (LCC-1)



Installation Guidelines

12/17/13

Safety and Health

Review the Material Safety Data Sheet (MSDS) before using this product. The MSDS contains important information concerning potential health hazards and protective measures for these hazards. Contact your supervisor or safety director to obtain a copy.

Storage Requirements

- For best performance, store the product in a dry location at temperatures between 60°F and 80°F.
- ANH packages its low cement castables in poly-lined paper bags or super sacks protected with plastic wrap to ensure dry product delivery. This packaging is not intended for outdoor storage. If no dry storage is available, contact your ANH sales and technical representative for alternate solutions.
- Always store low cement castables on a dry flooring surface to prevent ground moisture from condensing into the package.
- Avoid storage in direct sunlight to prevent the packaging from deteriorating over time.
- Ensure that your inventory is rotated on a regular basis. Low cement castables have an average shelf life of 3 to 6 months. Refer to the product data sheet for specific shelf life recommendations. If product usability is questionable due to age, consult your ANH sales and technical representative.
- Compaction during shipping and storage can cause soft lumps to form in the material. This is not detrimental to product performance if the lumps can easily be broken by hand.
- If the material becomes damp during shipping and storage, a partial reaction of the binders can occur causing hard lumps to form. If the lumps cannot easily be broken by hand, do not use the product without first consulting your ANH sales and technical representative.

Form and Backup Requirements

- Ensure that all casting forms are stout and watertight.
- Waterproof all porous forms, such as wood, and all porous backup linings before casting. Porous surfaces can reduce product properties and flow, resulting in a substandard installation.
- If installing over existing refractory, remove all loose material, debris, or contaminants prior to installation.
- Remove wood forms prior to dryout and heatup. Allowing wood forms to catch on fire can cause localized overheating and possible spalling of the refractory.

Mixer Requirements

- The product must be mixed in a high-intensity type mixer. ANH recommends high-intensity paddle mixers for best results. The use of low-intensity, poorly maintained mixing equipment or inadequate mixing times can result in a mix that appears too dry, prompting the operator to add an excessive amount of water.
- Mixing time will vary from mixer to mixer; a mixing time of 4 to 7 minutes is typically suggested.
- Clean all mixing and handling equipment prior to use. Residual material in the mixer may affect the set of the product.

Environmental Conditions

- For best results, ensure that the temperature of the product is between 60°F and 80°F prior to mixing. Temperature extremes affect working time, final set time, and final product quality.
- For hot weather installations, the mixing water may be cooled to extend working time.

Water Quality

For best results, use drinkable water with a pH of 6 to 7.5 and a temperature of 60°F to 80°F.

Low Cement Castables—Standard (LCC-1)



Installation Guidelines

Water Addition

- Accurate water measurement is critical to achieve proper installation and optimum product properties. Refer to the product data sheet for water specifications.
- Water must be measured by weight or by volume.
- The water requirements for low cement castables vary. The information given on the product data sheet is a target value. Mix the first batch at the target value, then adjust the amount of water in subsequent batches based on the required flow for the installation.
- Varying the amount of water more than .75% above or below the target value shown on the product data sheet is not recommended without consulting your ANH sales and technical representative.

Installation Methods

- The product is designed for vibration casting.
- Either form vibration or immersion (pencil) vibration can be used.
 - For form vibration, ensure that you can control the frequency and time of the vibration. Vibration should be sufficient to densify the product without causing the material to segregate. **Do not over-vibrate.**
 - For pencil vibration, insert the vibrator to the bottom of the casting. Move and extract the vibrator slowly to avoid creating an air pocket.
- Install the product promptly after mixing. Mixer and batch sizes should be as large as possible to minimize the number of batches.
- Never continue to install subsequent batches if the first batches start to set. If this occurs, use a cold joint casting design between the current casting and the subsequent casting.
- Do not trowel or slick the surface. This practice will prevent proper water removal during dryout.

Curing

- Ideal curing temperatures are between 70°F and 100°F.
- For installations above 60°F, cure the product for a minimum of 24 hours.
- For installations below 60°F, longer times are required to reach a hard set. Apply heat (not exceeding 120°F) to accelerate curing in cold conditions.
- Dryout and heatup can begin after the recommended minimum cure time as long as a hard set has been achieved.
- A hard set can be determined by striking the surface of the casting with a metal bar. A distinctive ring indicates a hard set.
- During curing, keep the surface covered and damp to avoid drying and cracking. Avoid direct water spray on the surface during curing.
- Avoid allowing the material to freeze prior to reaching a hard set or preferably prior to dryout (complete water removal).
- During curing, avoid applying excessive weight, such as equipment, to the cast surface.

Dryout

IMPORTANT: During dry out of a castable lining, only some water escapes via the hot face while most of the water is driven through to the cold face. If material is cast directly against a steel shell or other impermeable material without the use of weep holes, the water remaining in the lining will have no path to escape, and as the dry out schedule proceeds, internal steam pressure will rapidly increase resulting in probable lining damage and/or steam spalling. Dry out schedules issued by ANH assume that an unobstructed path exists through the cold face so that water can easily escape through the vessel/furnace shell. In most cases, weep holes are required to facilitate the removal of water/steam. Where weep holes are not allowed or a path to the weep holes is lengthy or not direct (such as a furnace hearth) some type of wicking should be used to create a path toward the weep holes or to the outside of the furnace.

Dryout and heatup can begin any time after a hard set has been achieved. Refer to the curing and dryout schedule specified on the product data sheet for more detailed information on the appropriate curing, dryout, and heatup procedures.

Tips

- When using metallic anchor systems, such as V-anchors, a coating on the tips is suggested to allow for anchor expansion during heatup.
- Wet down mixers and hoppers before beginning the mixing process.
- If your application requires weep holes, ensure that they are maintained before beginning installation.
- When using forms, apply a good mold release or grease before installation.
- Wash out all equipment as soon as installation is complete. A power washer is recommended.

Low Cement Castables—Standard (LCC-1)



Installation Guidelines

- Always time the mixing process. **Don't guess.**
- For water, less is always best. Don't guess. **Measure.**
- Never use additives such as set extenders or accelerators without first consulting your ANH sales and technical representative.